

TECHNICAL DATA SHEET

SWEDBOARD® FIBRE BROWN

| DIMENSIONS AND WEIGHT | | | | |
|---|--|-------|---|-----|
| Thickness | | mm | 10 | 16 |
| Weight per unit area | | kg/m² | 1.6 | 2.2 |
| Sheet sizes | | mm | As per delivery programme | |
| Sheet width tolerance | | mm | -0/+5 | |
| Sheet length tolerance | | mm | -0/+5 | |
| Sheet thickness tolerance | | mm | +/- 0.4 | |
| Tolerance in corner curvature from flat | | mm | <10 | |
| CORE | | | | |
| Paper cell core, FSC certified paper (FSC® C147499) | | | Brown | |
| SURFACE | | | | |
| Liner, FSC certified (FSC® C147499) | | | Premium kraftliner, brown, with transparent PE moisture barrier | |

Note: Technical data of our products are typical ones.

The actually measured values are subject to production variations.

Swedboard International AB does not guarantee the accuracy of the data provided and

disclaims liability for damages resulting from its use.

Product:

SWEDBOARD® Fibre Brown is a paper-based rigid board that offers a fully recyclable alternative for demanding POP and in-store signage applications. The engineered dust free core gives the material excellent strength and stability yet with light weight. The unique sealed surface helps keeping the material flat and prevents cracking when bending. Widths up to 2.5 metres enables increased productivity, reduced waste and unprecedented design flexibility. All materials are FSC certified (FSC® C147499).

Applications:

Displays (POS/POP)
Signage | Lettering
Shop design | Shop window decoration
Interior design | Furniture
Partitions | Cladding
Exhibition design and construction
Short term promotional campaigns



TECHNICAL DATA SHEET

SWEDBOARD® FIBRE BROWN

Processing:

Digital printing Screen printing Laminating Cutting Folding (V-groove)

Behaviour in external conditions:

- The material is not flame-retardant.
- The core is sensitive to moisture (only for indoor applications).

Storage - Transport - Handling

- SWEDBOARD® Fibre boards must be stored flat and protected from moisture and cold.
- Before processing, the paperboards require 24 hours to acclimatise to the processing environment.
- In order to avoid soiling surfaces, clean white cotton gloves should be worn.

Availability

- Please see our delivery programme for details.